



Product General Specifications

Base Material	Cross-linked polyolefin, Mylar .004" overlay	
Thickness	2mm (.080")	Finished thickness
MVTR	0.31 lbs / 1000 Sp. Ft. per 24 hrs.	Moisture barrier spec
R Value	3	Thermal resistance
Compression	29% @ 10.5 PSI	Resistance to compression
Tensile Strength	200 PSI	Breaking force required
Tear Resistance	28.0 lbs/in	Notched Breaking force
IIC	75*	
STC	73*	

***See "STC & IIC Straight Talk" publication included in dealer info binders, on our website or call our sales team for assistance.**

Product Standard Packaging spec's

Single rolls	43" x 28 Lin Ft.	(100 sf / roll)
Pallets	48 rolls per pallet	(4800 sf / pallet)

Distributed by:



Qualiwood Enterprises Inc. dba
ETM DISTRIBUTION

8411 Lougheed Highway, Burnaby, B.C. Canada V5A 1X3
 Tel: 1-866-421-0684 / Fax: 604-421-3948